

# Comparison of Fill Material Densities

## **Elastizell EF** - weight reducing chart

<b>Class I</b>	<b>18-24 pcf</b>
<b>Class II</b>	<b>24-30 pcf</b>
<b>Class III</b>	<b>30-36 pcf</b>
<b>Class IV</b>	<b>36-42 pcf</b>
<hr/>	
<b>Water</b>	<b>62.4 pcf</b>
<b>Lightweight Aggregates</b>	<b>60-90 pcf</b>
<b>Flowable Fills</b>	<b>90+ pcf</b>
<b>Soils</b>	<b>120 pcf</b>
<b>Aggregates, Asphalt</b>	<b>125 pcf</b>
<b>Lean Concrete</b>	<b>145 pcf</b>