

Sure-Seal/Sure-White FleeceBACK Adhered Roofing System

"Attachment II"

Direct Application Over Lightweight Insulating Concrete

May 2006

When specified, the Sure-Seal/Sure-White FleeceBACK membrane may be adhered directly to an **approved cellular or perlite lightweight insulating concrete** with a **minimum compressive strength of 200 psi** with Sure-Seal FAST Adhesive.

Note: When the use of vermiculite lightweight insulating concrete is specified, Carlisle must be contacted to determine applicable requirements pertaining to priming, venting and warranty wind speed coverage. Projects where the FleeceBACK membrane has been approved over vermiculite will be limited to a wind speed coverage of 55 mph peak gust wind speed unless otherwise approved by Carlisle.

The Authorized Applicator must provide Carlisle with a copy of a certification letter from the lightweight insulating concrete manufacturer (on new construction projects), which references the project name and location and contains the manufacturer's brand name, minimum compressive strength, average wet and air dry densities.

The substrate must be dry, free of debris, fins, frost, loose and foreign materials. Fill any gaps in the substrate greater than 1/4" with FAST Adhesive or other appropriate material.

Application Cautions

1. Do not proceed with membrane installation until the lightweight insulating concrete has cured a minimum of 48 hours. If necessary, consult with the lightweight insulating concrete manufacturer concerning additional drying time.
2. After rain or other precipitation, follow the manufacturer's requirements concerning proper visual inspection and additional drying time prior to adhering the membrane.
3. Prior to membrane installation, darker areas, especially along hairline cracks in the concrete, may serve as an indication of moisture entrapment and possible standing water beneath the surface. If this condition is found, consult with the lightweight insulating concrete manufacturer for proper corrective measures.
4. Except when lightweight insulating concrete is poured over slotted steel decks, the roofing applicator must conduct core cuts at the minimum rate of 1 every 2,000 square feet. The core cuts should be located around hairline cracks (if present) where darker areas are visible. After core cuts have been taken, the substrate must be examined for evidence of moisture above the structural deck and, if found, a wet/dry vacuum system, as recommended by the lightweight insulating concrete manufacturer, must be utilized to remove standing water from beneath the surface of the concrete.
 - a. To ensure the efficient operation of the vacuum system, a tight seal must be provided between the nozzle of the vacuum and the lightweight concrete substrate.
 - b. A one-way pressure relief vent, approved by Carlisle, must be installed over each core cut in accordance with Detail FB-8. Contact Carlisle for approved pressure relief vents.